

**DOCUMENT NUMBER:** CC231027TD

ISSUE DATE: October 27, 2023

## PRODUCT BULLETIN

**EFFECTIVE DATE** October 27, 2023

**SUBJECT** XPEL FUSION PLUS Ceramic Coating Resources for Applications

**APPLIES TO XPEL Dealers** 

## **DESCRIPTION**

Introducing the FUSION PLUS Dealer Guide - the ultimate handbook for FAQs, tips, tricks, and more concerning XPEL FUSION PLUS Ceramic Coatings. CLICK HERE to view the full guide.

What are the SKUs, volume, coating thickness, warranty length, flash time, dry time and cure time?

SKU	DESCRIPTION	SIZE	THICKNESS	WARRANTY	FLASH TIME	DRY TIME	FULL CURE TIME
R1450	PREMIUM	50 mL	0.9 mil	8 years	45-60 seconds	6 hours	72 hours
R1451	LITE	50 mL	0.2 mil	1 year	45-60 seconds	4 hours	72 hours
R1452	SATIN	50 mL	0.2 mil	4 years	30-60 seconds	4 hours	72 hours
R1364	PAINT & PPF	50 mL	0.3 mil	4 years	10-45 seconds	6 hours	72 hours
R1037	GLASS	50 mL	0.04 mil	2 years	10-30 seconds	24 hours	72 hours
R1372	UPHOLSTERY	16 oz	0.04 mil	2 years	N/A	1 hour	24 hours
R1373	PLASTIC & TRIM	50 mL	0.04 mil	1 year	10-45 seconds	24 hours	72 hours
R1374	WHEEL & CALIPER	50 mL	0.7 mil	3 years	10-45 seconds	24 hours	72 hours
R1370	MARINE	50 mL	0.7 mil	3 years	10-25 seconds	24 hours	96 hours
R1370-L	MARINE	275 mL	0.7 mil	3 years	10-25 seconds	24 hours	96 hours
R1453	AIRCRAFT	275 mL	0.9 mil	2 years	45-60 seconds	6 hours	72 hours

Note: Flash times will vary based on the temperature and humidity conditions of your shop. You may need to adjust timing based on your conditions +/- 15%. Final coating thickness might differ based on the application technique.

## Shelf Life:

- For PREMIUM, LITE, SATIN, PAINT & PPF, GLASS, AIRCRAFT, and WHEEL & CALIPER:
  - o 1 year unopened (stored properly)
  - o 14 days once opened (re-capped and stored properly)
- For UPHOLSTERY, PLASTIC & TRIM, and MARINE:
  - 1 year unopened (stored properly)
  - o 30 days once opened (re-capped and stored properly)

